


## Spiral SG® Fiber Glass Double Wall Insulation



### Description

Spiral SG Double Wall Insulation is a thermal and acoustical insulation designed for use in double wall spiral HVAC ducts. Spiral SG is made from rotary-process glass fibers bonded with a thermosetting resin.

### Advantages

Spiral SG is offered in a range of densities and thicknesses to optimize thermal and acoustical performance. It is made from rotary-process glass fibers bonded with a thermosetting resin, improving tensile strength and flexibility. The resilient fiber glass blanket is resistant to damage during transportation and fabrication.

### Uses

Spiral SG offers improved tensile strength and flexibility that make it ideal for insulating double wall HVAC Ducts.

### Thermal Conductivity

Type	Density		K Value 75°F (24°C) Mean Temp	
	PCF	KG/M <sup>3</sup>	BTU•in/(hr•ft <sup>2</sup> •°F)	W/M•°C
85	0.85	14	0.27	0.039
100	1.04	17	0.26	0.037
125	1.20	19	0.25	0.036
150	1.56	25	0.24	0.035

### Available Sizes

Type	Thickness		Frequency (Hz)							NRC**
	IN.	MM.	125	250	500	1000	2000	4000		
85	1	25	0.11	0.31	0.60	0.80	0.90	0.93	0.65	
	2	51	0.16	0.60	0.92	0.98	0.97	1.01	0.85	
100	1	25	0.09	0.30	0.60	0.77	0.89	0.93	0.65	
	2	51	0.18	0.64	0.99	1.02	1.01	1.04	0.90	
150	1	25	0.10	0.28	0.62	0.84	0.95	0.97	0.65	
	2	51	0.22	0.71	1.03	1.08	1.05	1.02	0.95	

### Specification Compliance

<b>ASTM</b>	E 84	<b>NFPA</b>	90A and 90B
<b>CAN/ULC</b>	S102-M88	<b>UL</b>	723

### Performance Specifications

Service Temp Max	350°F (177°C)
Corrosivity (ASTM C665)	Does not accelerate
Fire Hazard Classification	25/50 - Labels supplied when requested on order
Microbial growth (ASTM C1138)	Does not breed
Surface Burning Characteristics	Max Flame Spread 25 Max Smoke Developed Index 50
Water Sorption (ASTM C1104)	<5% by weight

### Sustainable Building Attributes

GREENGUARD®  
Certified



Recycled  
Content



GREENGUARD Certified products have been screened for more than 10,000 volatile organic compounds (VOCs) and meet stringent standards for low chemical emissions based on established criteria from key public health agencies.

### North American Sales Offices, Insulation Systems

**Eastern Region & Canada**  
P.O. Box 158  
Defiance, OH 43512  
(800) 334-2399  
Fax: (419) 784-7866

**Western Region and  
Outside North America**  
P.O. Box 5108  
Denver, CO 80217  
(800) 368-4431  
Fax: (303) 978-4661

The physical and chemical properties of the Spiral SG® RC High-Performance Air Duct Board listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you to ensure current information. **All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, including Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions, Limited Warranty and Limitation of Remedy, and information on other Johns Manville thermal insulation and systems, call (800) 654-3103.**



717 17th St.  
Denver, CO 80202  
1-800-654-3103  
WWW.JM.COM