

Gage No.	Lower Toler. Range (in)	Higher Toler. Range (in)	ASTM Range	Nominal Thickness (in)	Nominal lb/sf
10	0.1292	0.1472	0.018	0.1382	5.781
12	0.0994	0.1174	0.018	0.1084	4.531
14	0.0705	0.0865	0.016	0.0785	3.281
16	0.0575	0.0695	0.012	0.0635	2.656
18	0.0466	0.0566	0.01	0.0516	2.156
20	0.0356	0.0436	0.008	0.0396	1.656
22	0.0296	0.0376	0.008	0.0336	1.406
24	0.0236	0.0316	0.008	0.0276	1.156
26	0.0187	0.0247	0.006	0.0217	0.906
28	0.0157	0.0217	0.006	0.0187	0.781
30	0.0127	0.0187	0.006	0.0157	0.656