

METRIC FIBERGLAS™ PIPE INSULATION **FIBERGLASS** INSULATION

SSI II WITH ASI MAX



Description

Owens Corning® Metric Fiberglas® Pipe Insulation is molded of heavy density resin bonded inorganic glass fibers that come in one-piece, 36" (914mm) long, hinged sections. The insulation is tailored to fit for metric-sized copper, iron, PVC, and other polymer pipe applications.

Features

- ASJ Max is an all-service-jacket with a polymer film exterior surface that is smooth, durable, cleanable, wrinkle-resistant, resists water staining and doesn't support mold or mildew growth¹
- ASJ Max can resist short durations of water exposure that may occur during construction
- SSL II® Positive Closure System is an advanced double adhesion that fastens and installs with no need for staples or mastic
- · Insulation is tailored to fit with:
 - FlexCore technology to compress over copper and some small-bore iron pipes and fittings. saving time by eliminating the need to fillet
 - RigidCore technology for fast and easy fabrication on larger pipes
- Owens Corning is the only manufacturer to offer metric-sized fiberglass pipe insulation
- The product has a maximum operating temperature of 1,000°F (538°C) (with heat-up schedule)
- The product does not contain Polybromodiphenyl ethers (PBDE) (penta-, octa-, or deca-brominated diphenyl).



Standards, Codes Compliance

- ASTM C547. Mineral Fiber Pipe Insulation: Type I. Grade A: and Type IV. Grade B
- ASTM C585, Inner and Outer Diameters of Thermal Insulation for Nominal Sizes of Pipe and Tubing
- ASTM C1136, Flexible Low Permeance Vapor Retarders for Thermal Insulation: Types I. II. III. IV. X
- UL Labeled for Flame Spread Index of 25 or less and Smoke Developed Index of 50 and is fully building code compliant
- UL Listed and Labeled for use over PVC and other polymer pipes UL Category BSMP
- ASTM C795, Thermal Insulation for Use in Contact with Austenitic Stainless Steel⁴
- Nuclear Regulatory Commission Guide 1.36, Non-Metallic Thermal Insulation4
- MIL-PRF-22344E, Insulation, Pipe, Thermal, Fibrous Glass
- · MIL-DTL-32585, Type I, Form 4, Facing A
- MIL-DTL-24244D (Ships) Insulation Material with Special Corrosion, Chloride, and Fluoride Requirements⁴
- NFPA 90A and 90B

⁴Preproduction qualification testing complete and on file. Chemical analysis of each production lot required for total conformance. Certification needs to be specified at time of order.

PROPERTY	TEST METHOD	VALUE			
Density (size dependent)	ASTM C302	3.5 to 5.5 pcf			
Operating Temperature Range ²	ASTM C411	0°F to 1,000°F (-18°C to 538°C)			
Water Vapor Sorption	ASTM C1104	Less than 5% by weight			
Corrosion	ASTM C665	Pass – steel, copper, and aluminum			
Corrosion	ASTM C1617	Pass - steel			
Jacket Temperature Limitation	ASTM C1136	-20°F to 150°F (-29°C to 66°C)			
Jacket Permeance	ASTM E96, Proc. A	0.01 perm			
Burst Strength, min	ASTM D774/D774M	100 psi			
Composite Surface Burning Characteristics ³	UL 723, ASTM E84 or CAN/ULC-S201	Flame Spread 25 Smoke Developed 50			

^aWith heat-up schedule when operating temperatures between 850°F and 1,000°F. ^aThe surface burning characteristics of these products have been determined in accordance with UL 723, ASTM E84 or CAN/ULC-S102. Values are reported to the nearest 5 rating.

Applications

- Used to insulate iron, copper, PVC and other polymer pipes with operating temperatures between 0°F (-18°C) to 1,000°F (538°C) in commercial & institutional buildings, and industrial facilities
- When temperatures are above 650°F (454°C), maximum installed insulation thickness shall be no greater than 6" as a single layer or nested
- Rated per ASTM C547, Type I, Grade A Pipe insulation can be installed on in-service/hot pipes with an operating temperature up to 850°F (454°C)
- Rated per ASTM C547, Type IV, Grade B When operating temperatures will be between 850°F (454°C) to a 1,000°F (538°C) a heat-up schedule needs to be followed per the Installation Instructions, Pub No. 10021355
- When installed outdoors, an additional weather-protective jacket is required

Thermal Conductivity

MEAN TEMP °F	K BTU·IN/HR·FT ² •°F	MEAN TEMP °C	λ W/M•°C	
50	0.22	10	0.032	
75	0.23	25	0.034	
100	0.24	50	0.037	
150	0.27	100	0.043	
200	0.29	125	0.047	
250	0.32	150	0.051	
300	0.35	175	0.056	
350	0.39	200	0.062	
400	0.43	225	0.068	
450	0.48	250	0.075	
500	0.54	275	0.082	

Apparent thermal conductivity values determined in accordance with ASTM practice C1045 with data obtained by ASTM Test Method C335. Values are nominal, subject to normal testing and manufacturing tolerances.

Thickness to Prevent Surface Condensation

Owens Corning® ASJ Max Jacket for up to 16" NPS (400mm DN), in. (mm)^{5,6}

AMBIENT TEMP		RELATIVE	SYSTEM OPERATING TEMPERATURES					
٥F	(°C)	HUMIDITY	35°F	(2°C)	45°F	(7°C)	55°F	(13°C)
110	(43)	70%	1	(25)	1	(25)	1	(25)
		80%	11/2	(38)	11/2	(38)	11/2	(38)
		90%	31/2	(89)	31/2	(89)	3	(76)
100	(38)	70%	1	(25)	1	(25)	1	(25)
		80%	11/2	(38)	11/2	(38)	1	(25)
		90%	31/2	(89)	3	(76)	21/2	(64)
90	(32)	70%	1	(25)	1	(25)	1	(25)
		80%	11/2	(38)	1	(25)	1	(25)
		90%	31/2	(89)	3	(76)	21/2	(64)
80	(27)	80%	11/2	(38)	1	(25)	1	(25)
		90%	3	(76)	21/2	(64)	2	(51)
70	(21)	80%	1	(25)	1	(25)	1	(25)
		90%	21/2	(64)	2	(51)	1	(25)

⁵Calculations estimated using NAIMA 3E Plus version 4.0 software. Fixed design conditions: Steel Horizontal Piping, 16° NPS, 0 mph wind speed, Outer Surface Jacket Emittance of 0.9. ⁶Thermal conductivity values used in these calculations are subject to normal manufacturing tolerances.

Availability

Our Fiberglas™ Pipe Insulation portfolio is available in thicknesses up to 2" with inside diameters of 20 mm up to 315 mm. Contact your local Owens Corning Area Sales Manager for product availability.

Refer to Pipe Insulation Sizing Manual for more information: Pub. No. 10018078.

Installation

Ambient application temperatures are from 25°F (-4°C) to 110°F (43°C).

For complete installation instructions and recommendations see "Fiberglas™ Pipe Insulation Installation Instructions" (Pub. No. 10021355).

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- Certified by SCS Global Services to contain an average of 53% recycled glass content, 31% pre-consumer and 22% post-consumer
- For faced products: GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg
- Environmental Product Declaration (EPD) has been certified by UL Environment
- Material Health Certificate from Cradle to Cradle Products Innovation Institute







Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com. LEED® is a registered trademark of the U.S. Green Building Council.



OWENS CORNING INSULATING SYSTEMS. LLC

ONE OWENS CORNING PARKWAY TOLEDO, OHIO, USA 43659

www.owenscorning.com

Pub. No. 10022838. Printed in U.S.A. June 2019. © 2019 Owens Corning. All Rights Reserved.