



D. L. M. ADHESIVE 22-67

COLOR

Gray

SERVICE TEMPERATURE

-20° to 180° F
(-20° to 82°C)

COVERAGE

400 sq.ft/gal. (.1 Liter/m²)
The coverage rate is dependent on the machine setting.

WEIGHT PER GALLON

10.5 lbs

AVERAGE NONVOLATILE

51% by weight

BONDING TIME

0 to 17 minutes
The bonding time depends on the temperature, humidity, and the film thickness.

SAFETY

Flammability:
Wet: Non-flammable
Dry: See U.L. Classification. UL 723/ASTM E84

VISCOSITY

#6 at 50RPM RVT. 1800 to 3200 CPS

CAUTION:

Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. Do not take internally. In an emergency call a physician. Keep out of reach of children.

Meets requirements for LEED® IEQ Credit 4.1: Low Emitting Materials: Adhesives & Sealants.
MAX VOC= 0.005 lbs/gal. or .63 grams/liter, less water & exempt solvents.

WARRANTY TERMS: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. **WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE.** No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

DESCRIPTION

22-67 D.L.M. Adhesive is a water based adhesive designed for duct liner machines. It is a safe, economical adhesive for insulation applications that will also be mechanically fastened.

SPECIFICATION COMPLIANCE

Complies with LEED v4 ID&C, BD&C, Collaborative for High Performance Schools (CHPS) EQ 7.1.1, California Dept. of Public Health (CDPH) Standard Method v1.2, Criteria of MAS Certified Green® Program TVOC Emissions at 14 days, (Certificate Number MAS-1700746)

NFPA 90A& 90B
ASTM C916, Type I

METHOD OF APPLICATION

Roller, spray, duct liner machine

MATERIAL PREPARATION

Do not thin. Stir well.

LIMITATIONS

Keep from freezing
Apply between 40°F (4°C) and 110° F (43°C).

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Be sure surfaces are clean and dry. Apply the **22-67** to the sheet metal at a coverage rate of 400 sq. ft/gal. (.1 Liter/m²). Press the insulation into place. Immediately install the mechanical fasteners.

CLEANUP

Wet: Clean, fresh water.
DRY: Hot, soapy water or chlorinated solvent.

ASBESTOS FREE

UNDERWRITERS LABORATORIES, INC®
CLASSIFIED ADHESIVE
SURFACE BURNING CHARACTERISTICS
66H9

R10070 Applied to Inorganic Reinforced Cement Board		
	<u>USC</u>	<u>CNC</u>
Flame Spread	10	10
Smoke Developed	0	0
Tested as applied at a coverage rate of 100 sq. ft/gal (2.5m ² /L)		

MON-ECO INDUSTRIES, INC.

5 JOANNA COURT • EAST BRUNSWICK, NJ 08816 (732) 257-7942 • 800-899-6326 • FAX (732) 257-6525
Email: sales@mon-eco.com www.mon-ecoindustries.com

06/2017R

